

Data Sheet

HMEL R03RR



R03RR (Equivalent Novolen 1102 K) is a propylene homopolymer for extrusion and thermoforming applications. The extremely low water carry-over is of special advantage in the production of tapes

Properties (Typical Values)

Properties	Unit	Test method	Value
<u>Melt flow properties</u>			
MFR 230/2.16	g/10 min	ISO 1133	3.4
<u>Mechanical properties</u>			
Tensile modulus of elasticity (v = 1 mm/min)	MPa	ISO 527-2	1500
Tensile yield stress (v = 50 mm/min)	MPa	ISO 527-2	34
Tensile yield strain (v = 50 mm/min)	%	ISO 527-2	9
Tensile strain at break (v = 50 mm/min)	%	ISO 527-2	> 50
Charpy impact strength unnotched + 23 °C	kJ/m2	ISO 179/1eU	190
Charpy impact strength unnotched -30 °C	kJ/m2	ISO 179/1eU	16.5
Charpy impact strength notched + 23 °C	kJ/m2	ISO 179/1eA	4
Charpy impact strength notched -30 °C	kJ/m2	ISO 179/1eA	1.7
Ball indentation hardness (H 358/30)	MPa	ISO 2039-1	74
<u>Thermal properties</u>			
Melting point, DSC	°C	ISO 3146	163
Heat deflection temperature			0
- HDT/A (1.8 MPa)	°C	ISO 75-2	55
- HDT/B (0.45 MPa)	°C	ISO 75-2	85
Vicat softening temperature			0
- VST/A50 (10 N)	°C	ISO 306	154
- VST/B50 (50 N)	°C	ISO 306	90
<u>Other properties</u>			
Density	g/cm3	ISO 1183	0.91
<u>Applications</u>			
Thermoformed parts, Tape yarns, Monofilaments, Strapping			

"The information in this publication is submitted without prejudice, and is based on our current knowledge and experience and on a limited number of tests.

In view of the many factors that may affect processing and application, these data do not relieve the receiver of this information from the responsibility of carrying out their own tests and experiments; neither do they imply any legally binding assurance of certain properties or of suitability for a specific purpose of the products made with or on the basis of the information in this publication."